ARKEMA

11F ORIENTAL CHEMICAL BLDG, 50 SOGONG-DONG, JUNG-GU, SEOUL 100-718 KR



Altuglas: V040, V825A-100

Polymethyl Methacrylate (PMMA), pellets

Flammability	Value	Test Method
Flame Rating		
1.5 mm, NC	HB	UL 94
3.0 mm, NC	HB	UL 94
3.0 mm, NC	HB40	IEC 60695-11-10, -20
1.5 mm, NC	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	90.0 °C	
3.0 mm	90.0 °C	
RTI Imp		UL 746
1.5 mm	90.0 °C	
3.0 mm	90.0 °C	
RTI Str		UL 746
1.5 mm	90.0 °C	
3.0 mm	90.0 °C	

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 smallscale test data is intended solely for determining the flammability of plastic materials used in the components and parts of endproduct devices and appliances, where the acceptability of the combination is determined by UL.